

Basalt Roving 2400tex

Artikel-Nr. 010.2400.16.20 | 010.2400.16.05

USTER® TENSORAPID 4 3.0.0.0 UTR4 Thu 29.08.19 13:34 Operator I. Maechler Page 1

Catalog KUNDE1 Sample ID 044645 Material class Yarn
 Tests 1 / 20 v= 500 mm/min FV= 1200 cN LH= 500 mm P= 40 %

Standard Customer

Nom. count 2400 tex Style Multifilament Article 100% Basalt Mach. Nr. cone Nom. twist 0 T/m
 Uster Statistics
 Trial 6382 / Basalt Fibertec, Lotno 201903BA29,180,40%,manuel,m. Sinter Eins.

Total : 1 / 20 Single test(s)

Nr	Time to break s	B-Force N	Elong. %	Tenacity cN/tex	B-Work N.cm
Mean	1.77	1502	2.94	62.58	1029
s	0.14	111.4	0.23	4.64	172.4
CV	7.91	7.42	7.92	7.42	16.75
Q95	0.07	52.15	0.11	2.17	80.74
USP™					

